

SPARCAST 110C

SPARCAST 110C is a high strength, medium weight, abrasion resistant castable designed for applications where higher strength and good insulation is needed.

PHYSICAL PROPERTIES

Maximum Service Temperature	2500°F
Dry Castable Requirement	111 lbs./cu.ft.
Mix Water Required (by weight %)	14.0 – 15.0%
Bulk Density (at 230°F)	117 - 122 lbs./cu.ft
(at 1500°F)	111 - 115 lbs./cu.ft
Modulus of Rupture	
After Heating to 1500°F	900 - 1100 lbs/sq.in.
After Heating to 2000°F	800 - 1000 lbs/sq.in
Cold Crushing Strength	
After Heating to 1500°F	6000 - 9000 lbs/sq.in
After Heating to 2000°F	5000 - 8000 lbs/sq.in
Linear Change, %	
After Heating to 1500°F	-0.1 to -0.4%
After Heating to 2000°F	-0.1 to -0.4%
Erosion Resistance (ASTM C704)	
After Heating to 1500°F	Less than 15cc
Typical Chemical Analysis, %	
Al ₂ O ₃	48.8
SiO ₂	39.4
CaO	8.2
TiO ₂	0.8
Fe ₂ O ₃	1.4
MgO	0.5
Alkalies	1.3

SPARCAST 110C is available in 50# bags or 1000#, 1500#, 2000# bulk bags, palletized and shrink-wrapped. Store in a dry place.

Data shown are average results of standard ASTM tests unless otherwise noted. Results may vary subject to variations in manufacturing, testing, and installation procedures in the field.

P.O. Box 909, Jacksonville, AL36265

Phone: (256) 435-9342

Fax: (256) 435-9373